

**LAMINATI A FREDDO (UNI EN 10130)****TABELLE DI COMPARAZIONE**

<b>EUROPA</b>	<b>MAT.</b>	<b>I</b>	<b>D</b>	<b>E</b>	<b>F</b>	<b>GB</b>	<b>SE</b>	<b>USA</b>	<b>JAPAN</b>
EN 10130:07	N°	UNI EN 10130:91	DIN 1623/1:83	UNE 36083:75	NF A36-401:98	BS 1449/1:91	SIS:75	ASTM	JIS G 3141:96
DC 01	1.0330	Fe P01	St 12	AP 00	C	CR 4	14 11 42	A366CRCQ	SPCC
DC 03	1.0347	Fe P03	RRSt 13	AP 02	E	CR 2	14 11 48	A619CRDQ	SPCD
DC 04	1.0338	Fe P04	St 14	AP 04	ES	CR 1	14 11 47	A620CRDQSK	SPCE/SPCEN
DC 05	1.0312	Fe P05	(St 15)	-	SES	-	-	-	-
DC 06	1.0873	Fe P06	IF 181	-	-	-	-	-	-